

**Amendments to the Claims:**

The following listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Currently Amended) A heat resistant magnesium die casting alloy consisting ~~essentially~~ of, by wt%, the following composition:

Al: over 6% to not more than 10%,

Ca: over 2% to 5%,

Sr: 0.05% to 1.0%,

Mn: 0.1% to 0.6%, and

Bal: Mg and unavoidable impurities,

the Ca/Al ratio of the Ca content to the Al content being 0.3 to 0.5.

2. (Canceled)

3. (Original) A heat resistant magnesium die casting alloy as set forth in claim 1, wherein Ca: 2.5 to 3.5%.

4. (Canceled)

5. (Previously Presented) A die cast product comprised of a magnesium alloy as set forth in claim 1.

6-8. (Canceled)

9. (Previously Presented) A die cast product comprised of a magnesium alloy as set forth in claim 3.

10. (Currently Amended) A die cast product comprised of a magnesium alloy as set forth in ~~claim 4~~ claim 11.

11. (New) A heat resistant magnesium die casting alloy consisting of, by wt%, the following composition:

Al: over 6% to not more than 10%,

Ca: over 2% to 5%,

Sr: 0.05% to 1.0%,

Mn: 0.1% to 0.6%,

rare earth metal: 0.1% to 3%, and

Bal: Mg and unavoidable impurities,

the Ca/Al ratio of the Ca content to the Al content being 0.3 to 0.5.

12. (New) A heat resistant magnesium die casting alloy consisting of, by wt%, the following composition:

Al: over 6% to not more than 10%,

Ca: over 2.5% to 3.5%,

Sr: 0.05% to 1.0%,

Mn: 0.1% to 0.6%,

rare earth metal: 0.1% to 3%, and

Bal: Mg and unavoidable impurities,

the Ca/Al ratio of the Ca content to the Al content being 0.3 to 0.5